

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

MarFlex[®] 9659

HIGH DENSITY POLYETHYLENE

This HDPE is tailored for blown film applications that require:

- Outstanding water vapor barrier properties
- Excellent film strength and toughness for a homopolymer
- Paper-like film texture
- Excellent drawdown
- Excellent stiffness

Typical blown film applications include:

- Food packaging
- Coextrusions
- Overwraps
- Deli wrap
- Moisture barrier films

Nominal Resin Properties	English	SI	Method
Density	---	0.962 g/cm ³	ASTM D1505
Melt Index, 190C/2.16Kg	---	1 g/10min	ASTM D1238

Nominal Blown Film Properties at 1 mil	English	SI	Method
COF	0.25	0.25	ASTM D1894
Dart	---	50 g/mil	ASTM D1709
Elmendorf Tear MD	---	19 g/mil	ASTM D1922
Elmendorf Tear TD	---	210 g/mil	ASTM D1922
Tensile Strength at Break MD	6100 psi	42 MPa	ASTM D882
Tensile Strength at Break TD	3800 psi	26 MPa	ASTM D882
Tensile Strength Elongation at Break MD	490 %	490 %	ASTM D882
Tensile Strength Elongation at Break TD	550 %	550 %	ASTM D882
1% Secant Modulus MD	156000 psi	1076 MPa	ASTM D882
1% Secant Modulus TD	198000 psi	1365 MPa	ASTM D882
WVTR	0.26 g/100in ² /day	4 g/m ² /day	ASTM F1249
OTR	130 cm ³ /100in ² /day	2000 cm ³ /m ² /day	ASTM D3985

1. Produced using a grooved feed extruder at a rate of 8 lb/in die with a 2.5 BUR using a dual lip air ring

Revision Date June, 2004

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.