

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



PREMIUM EXTRUSION AND RIGID PACKAGING RESINS

Marlex[®] M368 Polyethylene

BLACK MEDIUM DENSITY POLYETHYLENE (MDPE) CONCENTRATE

This black masterbatch with its medium density polyethylene carrier resin has been formulated for pipe applications that require:

- Good long-term hoop strength
- Extended outdoor life
- Clean N550 carbon black

Let-down Guidelines

- Add M368 to the base pipe resin at a 15:1 let-down ratio to achieve a nominal 2.2 weight % carbon black concentration in the pipe.

Nominal Base Resin Properties ⁽¹⁾	English	SI	Method
Density	---	0.939 g/cm ³	ASTM D1505
Flow Rate (HLMI, 190 °C/21.6 kg)	---	20.0 g/10 min	ASTM D1238
Nominal Masterbatch Properties ⁽¹⁾	English	SI	Method
Density	---	> 1.0 g/cm ³	ASTM D1505
Flow Rate (HLMI, 190 °C/21.6 kg)	---	5.0 g/10 min	ASTM D1238
Carbon Black Loading	35.0 %	35.0 %	ASTM D1603

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on a compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1.

Revision Date: August, 2016

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.