

Omnix® DW-4050

high performance polyamide

Omnix® DW-4050 is a 50% glass-fiber reinforced high-performance polyamide. It is hot-water moldable and intended for use in components requiring superior mechanical properties even after moisture absorption.

Omnix® DW-4050 is characterized by high stiffness and strength, very good impact properties, good dimensional stability and high flow properties. This material is an economical alternative for drinking and potable water.

Omnix® DW-4050 is approved for use in potable water in France, Germany, United States and United Kingdom.

It processes readily using conventional injection molding machines and methods. Water-cooled molds are suitable for use with this grade.

- Black: Omnix® DW-4050 BK 001
- Natural: Omnix® DW-4050 NT 000

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• North America
Features	• Fast Molding Cycle • Good Dimensional Stability • Good Impact Resistance • Good Surface Finish • High Flow	• High Stiffness • High Strength • Hot Water Moldability • Paintable
Uses	• Appliances	• Food Service Applications
Agency Ratings	• ACS Unspecified Rating • DVGW W270 • EU Food Contact, Unspecified Rating ¹ • FDA Food Contact, Unspecified Rating ²	• KTW Guidelines • NSF STD-51 • WRAS Unspecified Rating
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	• Natural Color
Forms	• Pellets	
Processing Method	• Injection Molding	• Water-Heated Mold Injection Molding
Part Marking Code (ISO 11469)	• >(PA+PPA)-GF50<	

Physical	Dry	Conditioned	Unit	Test method
Density / Specific Gravity	1.59	--		ASTM D792
Molding Shrinkage ³				ISO 294-4
Across Flow	0.50	--	%	
Flow	0.10	--	%	

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus (23°C)	17000	17000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	245	205	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.6	2.6	%	ISO 527-2
Flexural Modulus	15000	--	MPa	ISO 178
Flexural Stress	350	--	MPa	ISO 178

Omnix® DW-4050

high performance polyamide

Impact	Dry	Conditioned	Unit	Test method
Charpy Notched Impact Strength (23°C)	13	13	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	100	95	kJ/m ²	ISO 179
Notched Izod Impact Strength (23°C)	15	15	kJ/m ²	ISO 180
Unnotched Izod Impact Strength (23°C)	90	85	kJ/m ²	ISO 180

Thermal	Dry	Conditioned	Unit	Test method
Melting Temperature	260	--	°C	ISO 11357-3

Additional Information

Dry	<ul style="list-style-type: none"> • Typical values shown tested on Dry as Molded samples. • Standard Packaging and Labeling: Omnix® DW-4050 resin is packaged in foil lined, multiwall paper bags containing 25 kg (55 pounds) of material. Individual packages will be plainly marked with the product number, the color, the lot number, and the net weight.
Conditioned	<ul style="list-style-type: none"> • Conditioned data generated according to test method ISO 1110.

Injection	Dry	Unit
Drying Temperature	80	°C
Drying Time	4.0 to 12	hr
Rear Temperature	250	°C
Front Temperature	285	°C
Processing (Melt) Temp	275 to 290	°C
Mold Temperature	80 to 140	°C

Omnix® DW-4050

high performance polyamide

Injection Notes

Drying:

- Omnix® DW-4050 resin is shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Omnix® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Omnix® processing guide. It should be dried before molding because excessive moisture content will result in reduced mechanical properties and processing issues, such as excessive nozzle drooling, foaming and splay visible on the molded parts.
- Recommended drying conditions are as follows:
 - Type of drier: Desiccant
 - Temperature: 80°C (175°F)
 - Time: 4-12 hours
 - Dew point: -30°C (-22°F) or lower
 - Polyamides oxidize in the presence of oxygen at high temperatures. Therefore drying temperatures above 80°C should be avoided, particularly for light colors or color-controlled parts.

Injection Molding:

- Omnix® DW-4050 resin can be readily injection molded in most screw injection molding machines. A general purpose screw is recommended, with minimum back pressure. The melt temperature should be between 275°C and 290°C (527°F and 554°F). Generally this can be achieved with barrel temperatures from 250°C (482°F) in the rear zone gradually increasing to 285°C (545°F) in the front zone. Mold temperature should be between 80° and 140°C (176° and 284°F).
- Set injection pressure to give rapid injection. Adjust holding pressure to one-half injection pressure. Set hold time to maximize part weight. Transfer from injection to hold pressure at the screw position just before the part is completely filled.

Storage:

- Omnix® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Omnix® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Omnix® processing guide.
-

Omnix® DW-4050

high performance polyamide

Notes

Typical properties: these are not to be construed as specifications.

¹ For specific clearances, please contact your Solvay representative.

² Omnix® DW-4050 is cleared for use under United States Food and Drug Administration (FDA) Conditions of Use B through H, in contact with all food types except Food Type VI C, Beverages containing more than 8 percent alcohol.

³ Solvay Test Method. Shrink rates can vary with part design and processing conditions. Please consult a Solvay Technical Representative for more information.

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.

