

Omnix® LF-4060 BK 000-9

high performance polyamide

Omnix® LF-4060 BK 000-9 is a 60% Long Glass Fiber reinforced, easy-flowing, heat stabilized HPPA with a very high flexural modulus. It exhibits unique stiffness/toughness combination, an excellent retention of properties in a wide temperature range, as well as outstanding creep and fatigue resistance.

Omnix® LF-4060 BK 000-9 has a pellet length of 9mm and can be processed on most injection-molding machines.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America	
Filler / Reinforcement	• Long Glass Fiber, 60% Filler by Weight		
Features	• Creep Resistant • Electrically Insulating • Fatigue Resistant • High Impact Resistance • High Temperature Stiffness	• Hot Water Moldability • Low CLTE • Low Shrinkage • Low Warpage	
Uses	• Aircraft Applications • Automotive Applications	• Consumer Applications • Industrial Applications	
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Dry	Conditioned	Unit	Test method
Density	1.69	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.10	--	%	Internal Method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.2	--	%	ISO 62

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus				ISO 527-2
23°C	22500	21000	MPa	
70°C	17000	--	MPa	
Tensile Stress				ISO 527-2
Break, 23°C	285	250	MPa	
Break, 70°C	200	--	MPa	
Tensile Strain (Break)	2.0	2.0	%	ISO 527-2
Flexural Modulus (23°C)	21500	--	MPa	ISO 178
Flexural Stress (23°C)	420	--	MPa	ISO 178

Impact	Dry	Conditioned	Unit	Test method
Charpy Notched Impact Strength (23°C)	45	40	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	110	110	kJ/m ²	ISO 179

Omnix® LF-4060 BK 000-9

high performance polyamide

Thermal	Dry	Conditioned	Unit	Test method
Heat Deflection Temperature				
0.45 MPa, Unannealed	260	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	255	--	°C	ISO 75-2/A
CLTE - Flow	1.8E-5	--	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.35	--	W/m/K	ISO 22007

Electrical	Dry	Conditioned	Unit	Test method
Electric Strength (2.00 mm)	35	--	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Surface Resistivity	1.0E+13	--	ohms/sq	ASTM D257

Additional Information

Conditioned • Conditioned data generated according to test method ISO 1110

Omnix® LF-4060 BK 000-9

high performance polyamide

Injection	Dry Unit
Drying Temperature	80 °C
Drying Time	4.0 to 12 hr
Suggested Max Moisture	0.10 %
Suggested Max Regrind	20 %
Rear Temperature	280 to 300 °C
Middle Temperature	285 to 300 °C
Front Temperature	285 to 300 °C
Nozzle Temperature	285 to 300 °C
Processing (Melt) Temp	< 320 °C
Mold Temperature	80 to 140 °C

Injection Notes

Pre-Drying -- Since polyamides are hygroscopic materials as well as sensitive to moisture during processing, this product should always be pre-dried.

Regrind -- Regrind of highly filled thermoplastic materials, such as this material, should only be recycled with special care. The regrind content must never exceed 20% and only regrind of optimum quality should be used. In any case, part properties should be checked.

Notes

Typical properties: these are not to be construed as specifications.

¹ Tested in accordance with S.O.P. methods

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.

