



## Guide to Molding WELLAMID<sup>®</sup> MRGF25/15 42H-BKJA6A Resin

Screw Machine	°F
Rear Zone	530-560
Middle Zone	520-540
Front Zone	510-530
Nozzle Temp	490-540
Melt Temp	520-570
Mold Temp	160-200
Injection Pressure	5,000-20,000 psi
Back Pressure	50 psi
Screw RPM	30-120

### **Drying:**

WELLAMID nylon resins shipped in bags are ready to mold with moisture content below 0.2%.

For opened bags and Gaylord boxes, material should be dried prior to molding for 2 to 4 hours at 175 °F. Circulating air ovens fitted with effective desiccant dehumidifying units, or vacuum ovens are best for drying WELLAMID resins.

The moisture content of the resin should be maintained at a level between 0.2% and 0.05% during molding to prevent hydrolytic degradation which manifests itself by splay marks, low physical properties, brittleness and nozzle drool.

**For further technical information call Wellman Technical Service at 248-645-0032.**