

## TECHNICAL DATA SHEET

### GRILAMID LVX-65H SST BLACK 9288

#### Product description

Grilamid LVX-65H SST black 9288 is a 65% glass fibre reinforced, heat stabilised engineering thermoplastic based on polyamide 12 for complex structural parts with the following product profile:

- Very high stiffness and strength
- Excellent impact and notched impact strength
- Excellent UV, heat and chemical resistance
- Very low moisture absorption
- Suitable for often repeated steam sterilisation
- Good flow characteristics
- High moulding precision, low warpage

Grilamid LVX-65H SST black 9288 is suitable for production of technical parts in application such as:

- Housings of electronic devices
- Automotive
- Mechanical engineering
- Safety components
- Housings of medical devices and instruments

**Grilamid®**  
**EMS**

## PROPERTIES

### Mechanical Properties

|                           |               | Standard      | Unit              | State        | Grilamid<br>LVX-65H SST<br>black 9288 |
|---------------------------|---------------|---------------|-------------------|--------------|---------------------------------------|
| Tensile E-Modulus         | 1 mm/min      | ISO 527       | MPa               | dry<br>cond. | 19'000<br>17'000                      |
| Tensile strength at break | 5 mm/min      | ISO 527       | MPa               | dry<br>cond. | 200<br>185                            |
| Elongation at break       | 5 mm/min      | ISO 527       | %                 | dry<br>cond. | 2.5<br>2.5                            |
| Impact strength           | Charpy, 23°C  | ISO 179/2-1eU | kJ/m <sup>2</sup> | dry<br>cond. | 85<br>85                              |
| Impact strength           | Charpy, -30°C | ISO 179/2-1eU | kJ/m <sup>2</sup> | dry<br>cond. | 80<br>80                              |
| Notched impact strength   | Charpy, 23°C  | ISO 179/2-1eA | kJ/m <sup>2</sup> | dry<br>cond. | 20<br>20                              |
| Notched impact strength   | Charpy, -30°C | ISO 179/2-1eA | kJ/m <sup>2</sup> | dry<br>cond. | 20<br>20                              |
| Ball indentation hardness |               | ISO 2039-1    | MPa               | dry<br>cond. | 210<br>190                            |

### Thermal Properties

|                                      |            |           |                     |     |        |
|--------------------------------------|------------|-----------|---------------------|-----|--------|
| Melting point                        | DSC        | ISO 11357 | °C                  | dry | 178    |
| Heat deflection temperature HDT/A    | 1.8 MPa    | ISO 75    | °C                  | dry | 175    |
| Heat deflection temperature HDT/C    | 8.0 MPa    | ISO 75    | °C                  | dry | 160    |
| Thermal expansion coefficient long.  | 23-55°C    | ISO 11359 | 10 <sup>-4</sup> /K | dry | 0.1    |
| Thermal expansion coefficient trans. | 23-55°C    | ISO 11359 | 10 <sup>-4</sup> /K | dry | 0.7    |
| Maximum usage temperature            | long term  | ISO 2578  | °C                  | dry | 90-120 |
| Maximum usage temperature            | short term | ISO 2578  | °C                  | dry | 150    |

### Electrical Properties

|                              |     |             |       |              |                  |
|------------------------------|-----|-------------|-------|--------------|------------------|
| Dielectric strength          |     | IEC 60243-1 | kV/mm | dry<br>cond. | 35<br>35         |
| Comparative tracking index   | CTI | IEC 60112   | -     | cond.        | 600              |
| Specific volume resistivity  |     | IEC 60093   | Ω · m | dry<br>cond. | 10 <sup>11</sup> |
| Specific surface resistivity |     | IEC 60093   | Ω     | cond.        | 10 <sup>12</sup> |

### General Properties

|                        |               |          |                   |     |      |
|------------------------|---------------|----------|-------------------|-----|------|
| Density                |               | ISO 1183 | g/cm <sup>3</sup> | dry | 1.70 |
| Flammability (UL94)    | 0.8 mm        | ISO 1210 | rating            | -   | HB   |
| Water absorption       | 23°C/sat.     | ISO 62   | %                 | -   | 0.8  |
| Moisture absorption    | 23°C/50% r.h. | ISO 62   | %                 | -   | 0.4  |
| Linear mould shrinkage | long.         | ISO 294  | %                 | dry | 0.05 |
| Linear mould shrinkage | trans.        | ISO 294  | %                 | dry | 0.30 |

Product-nomenclature acc. ISO 1874: PA12, MHR, 18-190, GF65

# Processing information for injection moulding of Grilamid LVX-65H SST black 9288

This technical data sheet for Grilamid LVX-65H SST black 9288 provides you with useful information on material preparation, machine requirements, tooling and processing.

## MATERIAL PREPARATION

Grilamid LVX-65H SST black 9288 is delivered dry and ready for processing in sealed, air tight packaging. Predrying is not necessary provided the packaging is undamaged.

### Storage

Sealed, undamaged bags can be kept over a period of time of at least one year when stored in facilities which are dry, protected from weather and where the bags are protected from damage.

### Handling and safety

Detailed information can be obtained from the "Material Safety Data Sheet" (MSDS) which can be requested with every material order.

### Drying

Grilamid LVX-65H SST black 9288 is dried and packed with a moisture content of  $\leq 0.10\%$ . Should the packaging become damaged or if it is left open too long, then the material must be dried. A too high moisture content becomes evident by a foaming melt, excessive nozzle drool and silver streaks on the moulded part.

Drying can be done as follows:

#### Desiccant dryer

|                        |              |
|------------------------|--------------|
| Temperature            | max. 80°C    |
| Time                   | 4 - 12 hours |
| Dew point of the dryer | -25°C        |

#### Vacuum oven

|             |              |
|-------------|--------------|
| Temperature | max. 100°C   |
| Time        | 4 - 12 hours |

### Drying time

If there is only little evidence of foaming of the melt or just slight silver streaks on the part, then the above mentioned minimal drying time will be sufficient. If material is stored open for days, shows strong foaming, unusually easy flow, streaks or a rough surface on the moulded part, then the maximum drying time is required.



Silver streaks can also be caused by overheating of the material (over 320°C) or by too long melt residence time in the barrel.

### Drying temperature

Polyamides are affected by oxidation at temperatures above 80°C in the presence of oxygen. Visible yellowing of the material is an indication of oxidation. Hence, temperatures above 80°C for desiccant dryers and temperatures above 100°C for vacuum ovens should be avoided.

At longer residence times (over 1 hour) hopper heating or a hopper dryer (80°C) is useful.

### Use of regrind

Grilamid LVX-65H SST black 9288 is a thermoplastic material. Hence, incomplete mouldings as well as sprues and runners can be reprocessed. The following points should be observed:

- Moisture absorption
- Grinding: Dust particles and particle size distribution
- Contamination through foreign material, dust, oil, etc.
- Level of addition to original material
- Colour variation
- Reduction of mechanical properties

When adding regrind, special care has to be taken by the moulder.

## MACHINE REQUIREMENTS

Grilamid LVX-65H SST black 9288 can be processed economically and without problems on all machines suitable for polyamides.

### Screw

Wear protected, universal screws with shut-off nozzles are recommended (3 zones).

#### Screw

|                   |             |
|-------------------|-------------|
| Length            | 18 D - 22 D |
| Compression ratio | 2 - 2.5     |

### Shot volume

The metering stroke (less decompression distance) must be longer than the length of the non-return-valve.

#### Selecting the injection unit

Shot volume = 0.5 - 0.8 x  
(max. shot volume of injection unit)

## Heating

At least three separately controllable heating zones, capable of reaching cylinder temperatures up to 350°C are recommended. Separate nozzle heating is necessary. The cylinder flange temperature must be controllable (cooling).

## Nozzle

Open nozzles are simple, allow an easy melt flow and are long lasting. After injection of the melt there is however, the danger that air is drawn into the barrel during retraction of the screw (decompression). For this reason, needle shut-off nozzles are often used.

## Clamping force

As a rule of thumb the clamping force can be estimated using the following formula:

### Clamping force

$$7.5 \text{ kN}^1) \times \text{projected area (cm}^2)$$

<sup>1)</sup> for a cavity pressure of 750 bar

## TOOLING

The design of the mould tool should follow the general rules for reinforced thermoplastics.

For the mould cavities common mould tool steel quality (e.g. hardened steel) which has been hardened to level of 56 HRC is necessary. We recommend additional wear protection in areas of high flow rates in the tool (e.g. pin point gates, hot runner nozzles).

## Demoulding / Draft angle

Asymmetric demoulding and undercuts have to be avoided if possible. Easy ejection can be achieved with many large pins or a stripper plate. Draft angles for the inner and outer wall between 0.5 and 3° is usually sufficient. Textured surfaces require a larger draft angle (1° per 0.025 mm depth of roughness).

| (VDI 3400)              | 12  | 15  | 18  | 21  | 24  | 27  |
|-------------------------|-----|-----|-----|-----|-----|-----|
| Depth of roughness (µm) | 0.4 | 0.6 | 0.8 | 1.1 | 1.6 | 2.2 |
| Demoulding angle (%)    | 1   | 1   | 1.1 | 1.2 | 1.3 | 1.5 |

| (VDI 3400)              | 30  | 33  | 36  | 39 | 42 | 45 |
|-------------------------|-----|-----|-----|----|----|----|
| Depth of roughness (µm) | 3.2 | 4.5 | 6.3 | 9  | 13 | 18 |
| Demoulding angle (%)    | 1.8 | 2   | 2.5 | 3  | 4  | 5  |

## Gate and runner

To achieve the best mould filling and to avoid sink marks, a central gate at the thickest section of the moulding is recommended. Pin point (direct) or tunnel gates are more economical and more common with technical moulding.

To avoid premature solidification of the melt and difficult mould filling, the following points should be considered:

### Gate diameter

0.8 x thickest wall section of the injection moulding part

### Runner diameter

1.4 x thickest wall section of the injection moulding part (but minimum 4 mm)

## VENTING

In order to prevent burn marks and improve weld line strength, proper venting of the mould cavity should be provided (dimensions of venting channels on the parting surface: Depth 0.02 mm, width 2 - 5 mm).

## PROCESSING

### Mould filling, post pressure and dosing

The best surface finish and a high weld line strength are achieved when a high injection speed and a sufficiently long post pressure time are employed.

The injection speed should be regulated so as to reduce towards the end of the filling cycle in order to avoid burning. For dosing at low screw revolutions and pressure the cooling time should be fully utilised.

### Basic machine settings

In order to start up the machine for processing Grilamid LVX-65H SST black 9288, the following basic settings are recommended:

### Temperatures

|        |            |
|--------|------------|
| Flange | 60-80 °C   |
| Zone 1 | 275 °C     |
| Zone 2 | 280 °C     |
| Zone 3 | 285 °C     |
| Nozzle | 280 °C     |
| Tool   | 80-100 °C  |
| Melt   | 270-290 °C |

### Pressures / Speeds

|                          |                            |
|--------------------------|----------------------------|
| Injection speed          | medium - high              |
| Hold-on pressure (spec.) | 500 - 1000 bar             |
| Dynamic pressure (hydr.) | 5 - 15 bar                 |
| Screw speed              | 50 - 100 min <sup>-1</sup> |

## CUSTOMER SERVICES

EMS-GRIVORY is a specialist in polyamide synthesis and the processing of these materials. Our customer services are not only concerned with the manufacturing and supply of engineering thermoplastics but also provide full technical support including:

- Rheological design calculation / FEA
- Prototype tooling
- Material selection
- Processing support
- Mould and component design

We are happy to advise you. Simply call one of our sales offices.

The recommendations and data given are based on our experience to date, however, no liability can be assumed in connection with their usage and processing.

Generated / updated: STA / 04.2009

This version replaces all previous product specific data sheets.

[www.emsgrivory.com](http://www.emsgrivory.com)