

TECHNICAL DATA SHEET

GRILON TSS/2 FA

General product description

Grilon TSS/2 FA is an unreinforced, heat stabilised, normal viscosity PA66 + PA6 injection moulding grade.

Grilon TSS/2 FA has the following important properties:

- Excellent flow behaviour
- High toughness
- Very good surface finish
- Easy processing

Grilon TSS is used typically for various applications in the automotive, the electro and the sports & leisure field such as loud-speaker grids, interior casings, chair rollers, handles and levers.

According to FDA (21 CFR 177.1500 and corresponding paragraphs covering the additives) GRILON TSS/2 FA is also approved for the direct contact with non-alcoholic food-stuffs.



PROPERTIES

Mechanical Properties		Standard	Unit	State	Grilon TSS/2 FA
Tensile E-Modulus	1 mm/min	ISO 527	MPa	dry cond.	3.300 1.400
Tensile strength at yield	5 mm/min	ISO 527	MPa	dry cond.	80 55
Elongation at yield	5 mm/min	ISO 527	MPa	dry cond.	4 15
Tensile at break	5 mm/min	ISO 527	%	dry cond.	65 55
Elongation at break	5 mm/min	ISO 527	%	dry cond.	5 >50
Impact strength	Charpy, 23°C	ISO 179/2-1eU	kJ/m ²	dry cond.	80 100
Impact strength	Charpy, -30°C	ISO 179/2-1eU	kJ/m ²	dry cond.	80 60
Notched impact strength	Charpy, 23°C	ISO 179/2-1eA	kJ/m ²	dry cond.	5 10
Notched impact strength	Charpy, -30°C	ISO 179/2-1eA	kJ/m ²	dry cond.	3 3
Ball indentation hardness		ISO 2039-1	MPa	dry cond.	140 80

Thermal Properties

Melting point	DSC	ISO 11357	°C	dry	260
Heat deflection temperature HDT/A	1.8 MPa	ISO 75	°C	dry	65
Heat deflection temperature HDT/B	0.45 MPa	ISO 75	°C	dry	200
Heat deflection temperature HDT/C	8.0 MPa	ISO 75	°C	dry	-
Thermal expansion coefficient long.	23-55°C	ISO 11359	10 ⁻⁴ /K	dry	0.6
Thermal expansion coefficient trans.	23-55°C	ISO 11359	10 ⁻⁴ /K	dry	1.0
Maximum usage temperature	long term	ISO 2578	°C	dry	70-100
Maximum usage temperature	short term	ISO 2578	°C	dry	200

Electrical Properties

Dielectric strength		IEC 60243-1	kV/mm	dry cond.	27 25
Comparative tracking index	CTI	IEC 60112	-	dry cond.	600 600
Specific volume resistivity		IEC 60093	Ω · m	dry cond.	10 ¹² 10 ¹¹
Specific surface resistivity		IEC 60093	Ω	cond.	10 ¹¹

General Properties

Density		ISO 1183	g/cm ³	dry	1.14
Flammability (UL94)	0.8 mm	ISO 1210	rating	-	HB
Water absorption	23°C/sat.	ISO 62	%	-	8
Moisture absorption	23°C/50% r.h.	ISO 62	%	-	2
Linear mould shrinkage	long.	ISO 294	%	dry	1.25
Linear mould shrinkage	trans.	ISO 294	%	dry	1.35

Product-nomenclature acc. ISO 1874: PA 66+6, MHR, 14-030 N

Processing information for the injection moulding of Grilon TSS/2 FA

This technical data sheet for Grilon TSS/2 FA provides you with useful information on material preparation, machine requirements, tooling and processing.

MATERIAL PREPARATION

Grilon TSS/2 FA is delivered dry and ready for processing in sealed, air tight packaging. Predrying is not necessary provided the packaging is undamaged.

Storage

Sealed, undamaged bags can be kept over a long period of time in storage facilities which are dry, protected from the influence of weather and where the bags can be protected from damage.

Handling and safety

Detailed information can be obtained from the "Material Safety Data Sheet" (MSDS) which can be requested with every material order.

Drying

Grilon TSS/2 FA is dried and packed with a moisture content of $\leq 0.10\%$. Should the packaging become damaged or be left open too long, then the material must be dried. A too high moisture content can be shown by a foaming melt, excessive nozzle drool and silver streaks on the moulded part.

Drying can be done as follows:

Desiccant dryer

Temperature:	max. 80°C
Time:	4 - 12 hours
Dew point of the dryer:	-25°C

Vacuum oven

Temperature:	max. 100°C
Time:	4 - 12 hours

Drying time

If there is only little evidence of foaming of the melt or just slight silver streaks on the part, then the above mentioned minimal drying time will be sufficient. If material is stored open for days, shows strong foaming, unusually easy flow, streaks or a rough surface on the moulded part, then the maximum drying time is required.



Silver streaks can also be caused by overheating of the material (over 350°C) or by too long melt residence time in the barrel.

Drying temperature

Polyamides are affected by oxidation at temperatures above 80°C in the presence of oxygen. Visible yellowing of the material is an indication of oxidation. Hence, temperatures above 80°C for desiccant dryers and temperatures above 100°C for vacuum ovens should be avoided. In order to detect oxidation it is advised to keep a small amount of granulate (light colours only !) as a comparison sample.

At longer residence times (over 1 hour) hopper heating or a hopper dryer (80°C) is useful.

Use of regrind

Grilon TSS/2 FA is a thermoplastic material. Hence, incomplete mouldings as well as sprues and runners can be reprocessed. The following points should be observed:

- Moisture absorption
- Grinding: Dust particles and particle size distribution
- Contamination through foreign material, dust, oil, etc.
- Level of addition to original material
- Colour variation
- Reduction of mechanical properties

When adding regrind, special care has to be taken by the moulder.

MACHINE REQUIREMENTS

Grilon TSS/2 FA can be processed economically and without problems on all machines suitable for polyamides.

Screw

Wear protected, universal screws with shut-off nozzles are recommended (3 zones).

Screw

Length:	18 D - 22 D
Compression ratio:	2 - 2.5

Shot volume

The metering stroke (less decompression distance) must be longer than the length of the non-return-valve.

Selecting the injection unit

Shot volume = $0.5 - 0.8 \times$
(max. shot volume of injection unit)

Heating

At least three separately controllable heating zones, capable of reaching cylinder temperatures up to 350°C. Separate nozzle heating is necessary. The cylinder flange temperature must be controllable (cooling).

Nozzle

Open nozzles are simple, allow an easy melt flow and are long lasting. There is however, the danger that during retraction of the screws following injection of the melt, air maybe drawn into the barrel (decompression). For this reason, needle shut-off nozzles are often used.

Clamping force

As a rule of thumb the clamping force can be estimated using the following formula:

Clamping force

$$7.5 \text{ kN}^{1)} \times \text{projected area (cm}^2\text{)}$$

¹⁾ for a cavity pressure of 750 bar

TOOLING

The design of the mould tool should follow the general rules for reinforced thermoplastics.

For the mould cavities common mould tool steel quality (e.g. hardened steel) which has been hardened to level of 56 HRC is necessary. We recommend additional wear protection in areas of high flow rates in the tool (e.g. pin point gates, hot runner nozzles).

Demoulding / Draft angle

Asymmetric demoulding and undercuts are to be avoided if possible. Generous provision should be made for ejection with many large pins or a stripper plate. Draft angles for the inner and outer wall between 0.5 and 3° is usually sufficient. Textured surfaces require a larger draft angle (1° per 0.025 mm depth of roughness).

(VDI 3400)	12	15	18	21	24	27
Depth of roughness (µm)	0.4	0.6	0.8	1.1	1.6	2.2
Demoulding angle (%)	1	1	1.1	1.2	1.3	1.5

(VDI 3400)	30	33	36	39	42	45
Depth of roughness (µm)	3.2	4.5	6.3	9	13	18
Demoulding angle (%)	1.8	2	2.5	3	4	5

Gate and runner

To achieve the best mould filling and avoid sink marks, a central gate at the thickest section of the moulding is recommended. Pin point (direct) or tunnel gates are more economical and more common with technical moulding.

To avoid premature solidification of the melt and difficult mould filling, the following points should be considered:

Gate diameter

0.8 x thickest wall section of the injection moulding part

Runner diameter

1.4 x thickest wall section of the injection moulding part (but minimum 4 mm)

VENTING

In order to prevent burning marks and improve weld line strength, proper venting of the mould cavity should be provided (venting channels on the parting surface dimensions: Depth 0.02 mm, width 2 - 5 mm).

PROCESSING

Mould filling, post pressure and dosing

The best surface finish and a high weld line strength are achieved when a high injection speed and a sufficiently long post pressure time are employed.

The injection speed should be regulated so as to reduce towards the end of the filling cycle in order to avoid burning. For dosing at low screw revolutions and pressure the cooling time should be fully utilised.

Basic machine settings

In order to start up the machine for processing Grilon TSS/2 FA , the following basic settings are recommended:

Temperatures

Flange	60 - 80°C
Zone 1	270°C
Zone 2	280°C
Zone 3	285°C
Nozzle	290°C
Tool	80 - 100°C
Melt	270 - 300°C

Pressures / Speeds

Injection speed	medium - high
Hold-on pressure (spec.)	300 - 800 bar
Dynamic pressure (hydr.)	5 - 15 bar
Screw speed	50 - 100 min ⁻¹

CUSTOMER SERVICES

EMS-GRIVORY is a specialist in polyamide synthesis and the processing of these materials. Our customer services are not only concerned with the manufacturing and supply of engineering thermoplastics but also provide full technical support including:

- Rheological design calculation / FEA
- Prototype tooling
- Material selection
- Processing support
- Mould and component design

We are happy to advise you. Simply call one of our sales offices.

The recommendations and data given are based on our experience to date, however, no liability can be assumed in connection with their usage and processing.

HEME/06.2008
www.emsgrivory.com