

[MatWeb](#), The Online Materials Database**EMS-Grivory Grilon AS Unreinforced Nylon 66 (Conditioned)****Subcategory:** Nylon; Nylon 66; Polymer; Thermoplastic**Material Notes:****Description:** General purpose unreinforced nylon 66 injection molding resin offering fast cycling and easy flow characteristics.**Application Examples:** Electrical components, automotive parts, internal appliance parts, power tool components and cable ties.

Data provided by EMS-Grivory.

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Water Absorption	1.3 %	1.3 %	24 hr immersion; ASTM D570
Moisture Absorption at Equilibrium	2 %	2 %	23°C/50% RH; DIN 53495
Water Absorption at Saturation	8 %	8 %	in water; DIN 53495
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	EMS
Linear Mold Shrinkage	0.024 cm/cm	0.024 in/in	Parallel; ASTM D955
Linear Mold Shrinkage, Transverse	0.015 cm/cm	0.015 in/in	EMS
Linear Mold Shrinkage, Transverse	0.027 cm/cm	0.027 in/in	ASTM D955
Mechanical Properties			
Hardness, Shore D	66	66	
Tensile Strength at Break	63 MPa	9140 psi	ASTM D638
Elongation at Break	300 %	300 %	ASTM D638
Flexural Modulus	0.72 GPa	104 ksi	ASTM D790
Flexural Strength	28 MPa	4060 psi	ASTM D790
Izod Impact, Notched	1.6 J/cm	3 ft-lb/in	ASTM D256
Electrical Properties			
Volume Resistivity	1e+013 ohm-cm	1e+013 ohm-cm	IEC 93
Surface Resistance	1e+012 ohm	1e+012 ohm	IEC 93
Dielectric Strength	27 kV/mm	686 kV/in	IEC 243-1
Comparative Tracking Index	600 V	600 V	IEC 112
Thermal Properties			
Melting Point	260 °C	500 °F	DSC
Maximum Service Temperature, Air	70 - 100 °C	158 - 212 °F	Long Term; EMS
Maximum Service Temperature, Air	200 °C	392 °F	Short Term; EMS
Deflection Temperature at 0.46 MPa (66 psi)	200 °C	392 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	64 °C	147 °F	ASTM D648
Flammability, UL94	HB	HB	0.8 mm

Processing Properties

Rear Barrel Temperature	255 °C	491 °F	
Middle Barrel Temperature	260 °C	500 °F	
Front Barrel Temperature	265 °C	509 °F	
Nozzle Temperature	255 - 265 °C	491 - 509 °F	
Melt Temperature	280 °C	536 °F	
Mold Temperature	80 °C	176 °F	
Drying Temperature	100 °C	212 °F	Vacuum Oven
Drying Temperature	80 °C	176 °F	Circulating Air Oven
Drying Temperature	80 °C	176 °F	Dehumidifying Dryer (dew point at -40°F)
Dry Time	6 - 16 hour	6 - 16 hour	Circulating Air Oven
Dry Time	4 - 16 hour	4 - 16 hour	Dehumidifying Dryer (dew point at -40°F)
Dry Time	4 - 16 hour	4 - 16 hour	Vacuum Oven

Copyright 1996-2006 by Automation Creations, Inc. The information provided by MatWeb is intended for personal, non-commercial use. The contents, results, and technical data from this site may not be reproduced either electronically, photographically or substantively without permission from Automation Creations, Inc. No warranty, neither expressed nor implied, is given regarding the accuracy of this information. The user assumes all risk and liability in connection with the use of information from MatWeb.