



组件 - 塑料
UL 档案号: E53898

EMS-CHEMIE AG
EMS CHEMIE HOLDING, VIA INNOVATIVA 1, DOMAT/EMS 7013 CH



Grivory: Grivory HTV-3H1

Polyamide (PA), pellets, glass reinforced

可燃性	值	测试方法
UL 阻燃等级		
0.75 mm, ALL	HB	UL 94
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
0.75 mm, ALL	HB75	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
热灯丝点火温度 (0.75 mm)	725 °C	IEC 60695-2-13
电气性能	值	测试方法
热丝引燃 (HWI) (0.75 mm)	PLC 4	UL 746
相比耐漏电起痕指数(CTI)	PLC 0	UL 746
热性能	值	测试方法
RTI Elec		UL 746
0.75 mm	150 °C	
1.5 mm	150 °C	
3.0 mm	150 °C	
RTI Imp		UL 746
0.75 mm	140 °C	
1.5 mm	140 °C	
3.0 mm	140 °C	
RTI		UL 746
0.75 mm	140 °C	
1.5 mm	140 °C	
3.0 mm	150 °C	