

Property	Test Condition	Test Method ISO	Units	GF + Mineral filler reinforced
				High filler, High strength
				A400M-X05
				>PPS-GF+MD60<
Physical property				
Water Absorption	24hrs. in 23°C water	ISO62	%	0.02
Density	23°C	ISO1183	kg/m ³	1820
Color				Black
Mechanical property				
Tensile strength	23°C	ISO527-1,2	MPa	165
Elongation at Break	23°C	ISO527-1,2	%	1.1
Flexural Strength	23°C	ISO178	MPa	250
Flexural Modulus	23°C	ISO178	GPa	18.5
Coefficient of friction	Vs metal	-	-	-
Shear Strength	23°C	JIS K7214	MPa	-
Rockwell Hardness		ISO2039-2	R Scale	122
Taper Abrasion		ISO9352	mg/1000times	-
Charpy Impact Strength (V-notched)	23°C	ISO179	kJ/m ²	9
Charpy Impact Strength (Unnotched)	23°C	ISO179	kJ/m ²	25
Heat property				
Melting Point		ISO11357-3	°C	278
Coef of Linear Thermal Expansion	Machine Direction	ISO11359-2	×10 ⁻⁵ /K	1.8
Coef of Linear Thermal Expansion	Transverse Direction	ISO11359-2	×10 ⁻⁵ /K	3
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	°C	260
Flammability		UL94	rank/thickness mmt	V-0(0.36mmt)
Electrical property				
Volume Resistivity		IEC60093	Ω · m	10 ¹⁴
Dielectric Strength		IEC60243-1	MV/m	20
Dielectric Constant	23°C、60%RH、1MHz	IEC 60250	-	4.9
Dissipation Factor	23°C、60%RH、1MHz	IEC 60250	-	0.002
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.2
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.75
Bar Flow	320°C,98MPa,1mmt	Toray Method	×10 ⁻³ m	110
PDF DOWNLOAD				

Applications of torelina

Automobile