



# Thermylene® P-10FG-2100

Asahi Kasei Plastics North America Inc. - Polypropylene

Wednesday, July 29, 2015

## General Information

### Product Description

PP-GF10  
10% Glass Fiber Reinforcement

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Filler / Reinforcement	• Asia Pacific • Latin America • Glass Fiber, 10% Filler by Weight		
Automotive Specifications	• FORD ESB-M4D299-A		

## ASTM & ISO Properties <sup>1</sup>

	Nominal Value	Unit	Test Method
Physical			
Density	0.980	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Mechanical			
Tensile Stress	6670	psi	ISO 527-2
Flexural Modulus	348000	psi	ISO 178
Flexural Stress	10200	psi	ISO 178
Impact			
Charpy Notched Impact Strength	2.3	ft-lb/in <sup>2</sup>	ISO 179
Notched Izod Impact Strength	2.7	ft-lb/in <sup>2</sup>	ISO 180/A
Thermal			
Heat Deflection Temperature (66 psi, Unannealed)	309	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	230	°F	ISO 75-2/A

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.