

Thermylene® P-9900-0712

聚丙烯

Asahi Kasei Plastics North America Inc.

PROSPECTOR®

www.ulprospector.com

Technical Data

产品说明

PP
Unreinforced

总体

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet (English)		
搜索 UL 黄卡	• Asahi Kasei Plastics North America Inc.		
供货地区	• 北美洲 • 非洲和中东	• 拉丁美洲 • 欧洲	• 亚太地区

物理性能	额定值	单位制	测试方法
密度	0.910	g/cm³	ISO 1183/A
熔流率 (熔体流动速率) (230°C/2.16 kg)	17	g/10 min	ISO 1133
机械性能	额定值	单位制	测试方法
拉伸应力	33.0	MPa	ISO 527-2
弯曲模量	1800	MPa	ISO 178
弯曲应力	46.0	MPa	ISO 178
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度	5.0	kJ/m²	ISO 179
悬臂梁缺口冲击强度	5.6	kJ/m²	ISO 180/A
热性能	额定值	单位制	测试方法
热变形温度 (1.8 MPa, 未退火)	60.0	°C	ISO 75-2/A

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。



Thermylene® P-9900-0712

聚丙烯

Asahi Kasei Plastics North America Inc.

PROSPECTOR®

www.ulprospector.com

购买地点

供应商

Asahi Kasei Plastics North America Inc.

Fowlerville, MI USA

电话: 517-223-2000

Web: <http://www.asahikaseiplastics.com/>

分销商

Entec Polymers

电话: 800-375-5440

Web: <http://www.entecpolymers.com/>

供货地区: North America

Plastics Plus, Inc.

电话: 248-393-0300

Web: <http://www.plasplus.com/>

供货地区: North America

PolyOne Distribution

PolyOne Distribution is a global distribution company. Contact PolyOne Distribution for availability of individual products by country.

电话: 800-894-4266

Web: <http://polyonedistribution.com/>

供货地区: Global

PolySource

电话: 866-558-5300

Web: <http://www.polysource.net/>

供货地区: North America

