



Thermylene® P4-9900-0520

Asahi Kasei Plastics North America Inc. - Polypropylene

Wednesday, July 29, 2015

General Information

Product Description

PP-FR
Unreinforced with Flame Retardant (FR)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Flame Retardant		
Features	• Flame Retardant		
Automotive Specifications	• GM GMW16783P-PP-FR(17)		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	3630	psi	ISO 527-2
Flexural Modulus	232000	psi	ISO 178
Flexural Stress	5510	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.5	ft-lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	205	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	131	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.