



## TECHNICAL DATA SHEET

Product Type

**HDPE Compound for Blow molding Tank**

Product Name

**SCG HDPE**

Product Grade

**H800BBL**

### Product Description

SCG HDPE H800BBL is a blue color compound, high density polyethylene resin that is specially designed for large water tanks. It provides excellent mechanical properties and process ability. Well dispersed stabilizer and anti-oxidant provide high thermal stability. Fully UV stabilizers package design for outdoor application.

### Typical Application

- Water Tank

### Product Characteristics

- Good process ability
- High Thermal stability
- Outstanding mechanical strength
- Good UV protection

### Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 190 °C, 5.0 kg	0.27	g/10 min
Melt Flow Rate	ASTM D 1238 @ 190 °C, 21.6 kg	10.90	g/10 min
Density	ASTM D 1505	0.953	g/cm <sup>3</sup>
Tensile Strength at Yield	ASTM D 638*	25	MPa
Tensile Strength at Break	ASTM D 638 *	> 35	MPa
Elongation at Break	ASTM D 638*	> 750	%
Flexural Modulus	ASTM D 790	> 850	MPa
Notched Izod Impact	ASTM D 256 @ 23 °C	290	J/m
Oxidative induction time	ISO 11357-6 @ 210 °C	> 30	min
Hardness	ASTM D 2240	62	Shore D
ESCR	ASTM D 1693 @ 10% Igepal B	>5000	Hrs, FO
Vicat Softening Temperature	ASTM D 1525	122.4	°C

\* Crosshead speed is 100 mm/min

**Note:** the given values are typical value measured on the product. Values herein are not to be construed as a product Specification.



## TECHNICAL DATA SHEET

Product Type

**HDPE Compound for Blow molding Tank**

Product Name

**SCG HDPE**

Product Grade

**H800BBL**

### Processing

For extrusion of SCG HDPE H800BBL, it is recommended to use a screw giving good melting and mixing without excessive shear. A single or double flight PE screws have proven satisfactory and will be used with good result. For normal extrusion equipment, we suggest a melt temperature of 190 – 220 °C .

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

### Product Available Form

- Color Pellet

### Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container

### Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odor generation and color changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.

### Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.



## TECHNICAL DATA SHEET

Product Type

**HDPE Compound for Blow molding Tank**

Product Name

**SCG HDPE**

Product Grade

**H800BBL**

### Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

### Related

- The latest version of this document will be available at our website, [www.scgchemicals.com](http://www.scgchemicals.com), or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Material Safety Datasheet
  - Statement on compliance to food contact regulations

### Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.