



TECHNICAL DATA SHEET

Product Type

Polypropylene Impact Copolymer

Product Name

SCG PP

Product Grade

P842J

Product Description

SCG PP P842J is a high flow ability impact copolymer polypropylene resin designed for injection molding process. This resin is recommended for product that requires very high stiffness and very high processability.

Typical Application

- Automotive parts
- Home appliance parts
- Complicated Industrial parts
- Any parts require good flow ability

Product Characteristics

- High stiffness and processability
- Good impact strength

International

- U.S FDA 21 CFR 177.1520
- UL Yellow Card E202743
- RoHS Directive 2011/65/EU

Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230°C, 2.16 kg	40	g/10 min
Density	ASTM D 1505	0.910	g/cm ³
Tensile Strength at Yield	ASTM D 638 @ Speed 50 mm/min	295	kg/cm ²
Tensile Strength at Break	ASTM D 638 @ Speed 50 mm/min	180	kg/cm ²
Flexural Modulus	ASTM D 790	14,500	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23°C	74	J/m
Notched Izod Impact	ASTM D 256 @ 0°C	49	J/m
Notched Izod Impact	ASTM D 256 @ -20°C	30	J/m
Rockwell Hardness	ASTM D 785	80	R-Scale
Melting Point	ASTM D 2117	163	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	120	°C
Flammability	UL - 94	HB	-

Note: the given values are typical values measured on the product. Values herein are not to be constructed as a product specification.



TECHNICAL DATA SHEET

Product Type

Polypropylene Impact Copolymer

Product Name

SCG PP

Product Grade

P842J

Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 230-270°C

Mold temperature: 25-70°C

Injection speed: Fast

Pressure (of Max. Pressure):

Injection 40-80%

Packing and Holding 30-60%

Back 10%

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Block pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical services.



TECHNICAL DATA SHEET

Product Type

Polypropylene Impact Copolymer

Product Name

SCG PP

Product Grade

P842J

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical services.

Related

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Plastics/SCG Performance Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Safety Data Sheet (SDS)
 - Statement on compliances

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.