



## TECHNICAL DATA SHEET

Product Name

**SCG PP**

Product Type

**Polypropylene Impact Copolymer**

Product Grade

**P483JU**

### Product Description

SCG PP P483JU is a developmental of high stiffness polypropylene impact copolymer product which contains anti-static agent and UV stabilizer. It is designed for very high stiffness, creep resistance, and high heat resistance while maintain a good impact strength than those of general impact copolymer polypropylene and suitable for injection molding application.

### Typical Application

- Returnable transport packaging such as Pallet, Crate and Container
- Automotive parts
- Electrical appliance parts
- Any parts require outdoor uses agent

### Product Characteristic

- Excellent stiffness
- High impact strength
- Good processibility
- Good dimension stability
- High heat resistance
- Good UV resistance
- Contained anti-static agent

### International Compliance

- RoHS Directive 2011/65/EU
- REACH Regulation (EC) 1907/2006

### Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230 °C, 2.16 kg	5	g/10 min
Density	ASTM D 1505	0.91	g/cm <sup>3</sup>
Tensile Strength at Yield	ASTM D 638 @ Crosshead speed 50 mm/min	300	kg/cm <sup>2</sup>
Flexural Modulus	ASTM D 790	16,500	kg/cm <sup>2</sup>
Notched Izod Impact	ASTM D 256 @ 23°C	108	J/m
Notched Izod Impact	ASTM D 256 @ 0°C	69	J/m
Notched Izod Impact	ASTM D 256 @ -20°C	59	J/m
Melting Point	ASTM D 2117	166	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm <sup>2</sup>	125	°C

### Note:

- Conversion factor for changing unit from kg/cm<sup>2</sup> to MPa is divided by 10.20
- The given values are typical value measured on the product. Values herein are not to be construed as a product specification.

### Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 210-250°C

Mold temperature: 25-70°C

Injection speed: Fast

Screw speed 40-70 rpm

Pressure: Injection 40-80%

Packing and Holding 30-60%

Back 10% of Max Pressure

SCG Plastics Co., Ltd.

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand

Tel. +66 2586 4874

Fax +66 2586 5522

E-mail: general\_plastics@scg.com

Page | 1

Published: May 2019

[www.scgchemicals.com](http://www.scgchemicals.com)



## TECHNICAL DATA SHEET

Product Name	SCG PP
Product Grade	P483JU

Product Type

**Polypropylene Impact Copolymer**

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

#### Product Available Form

- Block pellet
- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container
- 750 kg big bag

#### Product Packaging

#### Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.

#### Safety

- The product is not classified as a hazardous material.
- Please see our Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

#### Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Safety Data Sheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

#### SCG Plastics Co., Ltd.

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand  
Tel. +66 2586 4874      Fax +66 2586 5522  
E-mail: general\_plastics@scg.com

Page | 2  
Published: May 2019

[www.scgchemicals.com](http://www.scgchemicals.com)



## TECHNICAL DATA SHEET

Product Type

**Polypropylene Impact Copolymer**

Product Name

**SCG PP**

Product Grade

**P483JU**

### Related Documents

- The latest version of this document will be available at our website, [www.scgchemicals.com](http://www.scgchemicals.com), or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Safety Data Sheet
  - Statement on compliance

### Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.