

Property	Test Condition	Test Method ISO	Units	Nylon610	
				Heat stability	
				CM2006	
				>PA610<	
				Dry	1.5%water
Physical property					
Water Absorption	24hrs. in 23℃ water	ISO62	%	0.3	-
Water Absorption	23℃ in water	ISO62	%	4	-
Density	23℃	ISO1183	kg/m ³	1080	
Mechanical property					
Tensile strength	-40℃	ISO527-1,2	MPa	-	-
Tensile strength	23℃	ISO527-1,2	MPa	60	-
Tensile strength	80℃	ISO527-1,2	MPa	-	-
Elongation at Yield	23℃	ISO527-1,2	%	-	-
Elongation at Break	23℃	ISO527-1,2	%	50	50
Flexural Strength	-40℃	ISO178	MPa	-	-
Flexural Strength	23℃	ISO178	MPa	95	-
Flexural Strength	80℃	ISO178	MPa	-	-
Flexural Modulus	-40℃	ISO178	GPa	-	-
Flexural Modulus	23℃	ISO178	GPa	2	-
Flexural Modulus	80℃	ISO178	GPa	-	-
Compressive Strength	23℃	ISO604	MPa	-	-
Coefficient of friction (Without lubrication)	Vs metal	Suzuki Method	-	-	-
Shear Strength	23℃	ASTM D732	MPa	50	-
Rockwell Hardness	23℃	ISO2039-2	R Scale	116	-
Rockwell Hardness	80℃	ISO2039-2	R Scale	-	-
Taper Abrasion		ISO9352	mg/1000times	-	-
Charpy Impact Strength (V-notched)	-40℃	ISO179	kJ/m ²	-	-
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	40	-
Charpy Impact Strength (Unnotched)	-40℃	ISO179	kJ/m ²	-	-
Charpy Impact Strength (Unnotched)	23℃	ISO179	kJ/m ²	破断せず	破断せず
Heat property					
Melting Point		DSC Method	℃	225	-
Specific Heat		-	J/g・℃	1.9	-
Thermal Conductivity		-	W/m・℃	0.25	-
Coef of Linear Thermal Expansion		ISO11359-2	×10 ⁻⁵ /℃	12	-
Heat Deflection Temp Low Load	0.45MPa	ISO75-1,2	℃	180	-
Flammability		UL94	rank/thickness m mt	自己消火性	自己消火性
Electrical property					
Volume Resistivity		IEC60093	Ω・m	10 ¹¹ ~10 ¹²	-
Dielectric Strength		IEC60243-1	MV/m	-	-
Dielectric Constant	23℃、60% RH、50Hz	IEC 60250	-	-	-
Dielectric Constant	23℃、60% RH、1KHz	IEC 60250	-	-	-
Dielectric Constant	23℃、60% RH、1MHz	IEC 60250	-	-	-
Dissipation Factor	23℃、60% RH、50Hz	IEC 60250	-	-	-
Dissipation Factor	23℃、60% RH、1KHz	IEC 60250	-	-	-
Dissipation Factor	23℃、60% RH、1MHz	IEC 60250	-	-	-
IEC Tracking Index(CTI)		UL-746B	-	-	-
Arc resistance	Tungsten Electrode	UL-746A	sec.	-	-
Molding property					
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	-	-
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	-	-

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.