

Property	Test Condition	Test Method ISO	Units	Nylon66/Abrasion Resistance	
				GF30%	
				CM3003G30	
				>PA66-GF30+XD<	
				Dry	
Physical property					
Water Absorption	24hrs. in 23℃ water	ISO62	%	0.6	
Water Absorption	23℃ in water	ISO62	%	5.5	
Density	23℃	ISO1183	kg/m ³	1380	
Mechanical property					
Tensile strength	-40℃	ISO527-1,2	MPa	-	
Tensile strength	23℃	ISO527-1,2	MPa	170	
Elongation at Break	-40℃	ISO527-1,2	%	-	
Elongation at Break	23℃	ISO527-1,2	%	3	
Elongation at Break	80℃	ISO527-1,2	%	-	
Flexural Strength	-40℃	ISO178	MPa	-	
Flexural Strength	23℃	ISO178	MPa	270	
Flexural Modulus	-40℃	ISO178	GPa	-	
Flexural Modulus	23℃	ISO178	GPa	10	
Coefficient of friction (Without lubrication)	Vs metal	Suzuki Method	-	0.2	
Rockwell Hardness	23℃	ISO2039-2	R Scale	121	
Taper Abrasion		ISO9352	mg/1000times	23	
Charpy Impact Strength (V-notched)	-40℃	ISO179	kJ/m ²	-	
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	10	
Charpy Impact Strength (Unnotched)	-40℃	ISO179	kJ/m ²	-	
Heat property					
Melting Point		DSC Method	℃	265	
Coef of Linear Thermal Expansion		ISO11359-2	×10 ⁻⁵ /℃	2~3	
Heat Deflection Temp Low Load	0.45MPa	ISO75-1,2	℃	262	
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	℃	255	
Flammability		UL94	rank/thickness m mt	HB	
Molding property					
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.2~0.5	
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.6~0.8	

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.