

Property	Test Condition	Test Method ISO	Units	Reinforced
				Good Appearance, GF15%
				1101G-X53
				>PBT+P-GF15<
Physical property				
Density	23℃	ISO1183	kg/m ³	1440
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	97
Elongation atBreak	23℃	ISO527-1,2	%	2.7
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	5
Heat property				
Flammability		UL94	rank/thickness m mt	HBEquivalent

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.