

Property	Test Condition	Test Method ISO	Units	Flame retardant reinforced
				High toughness, GF30%, V-0
				1184G-A30 N1
				>PBT-I-GF30-FR(17)<
Physical property				
Water Absorption	24hrs. in 23℃ water	ISO62	%	0.07
Density	23℃	ISO1183	kg/m ³	1630
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	140
Elongation at Break	23℃	ISO527-1,2	%	2.5
Tensile Modulus	23℃	ISO527-1,2	GPa	10
Flexural Strength	23℃	ISO178	MPa	220
Flexural Modulus	23℃	ISO178	GPa	9.5
Coefficient of friction (Without lubrication)	Vs metal	Suzuki Method	-	0.15
Coefficient of friction	Vs metal	-	-	0.2
Rockwell Hardness	23℃	ISO2039-2	R Scale	M85
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	9
Charpy Impact Strength (Unnotched)	23℃	ISO179	kJ/m ²	65
Heat property				
Coef of Linear Thermal Expansion	-30~100℃	ISO11359-2	×10 ⁻⁵ /℃	4.1
Heat Deflection Temp Low Load	0.45MPa	ISO75-1,2	℃	220
Heat Deflection Temp High Load	1.82MPa	ISO75-1,2	℃	207
Flammability		UL94	rank/thickness m mt	V0(1/64")
Electrical property				
Volume Resistivity		IEC60093	Ω · m	1.1x10 ¹⁵
Dielectric Strength		IEC60243-1	MV/m	14
Dielectric Constant	23℃、60%RH、50Hz	IEC 60250	-	4
Dielectric Constant	23℃、60%RH、1KHz	IEC 60250	-	3.8
Dissipation Factor	23℃、60%RH、50Hz	IEC 60250	-	0.001
Dissipation Factor	23℃、60%RH、1MHz	IEC 60250	-	0.02
CTI		UL 746A	UL Index	2
Arc resistance	W electrode	IEC60950	sec	134
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.3
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.9
Bar Flow	250℃,93MPa,1mmt	Toray Method	×10 ⁻³ m	136

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.