

Property	Test Condition	Test Method ISO	Units	Flame retardant reinforced	
				Heat cycle resistance, GF20%, V-0	
				5174G-X11	
				>PBT-I-GF20-FR(17)<	
Physical property					
Water Absorption	24hrs. in 23℃ water	ISO 62	%	0.07	
Density	23℃	ISO 1183	kg/m ³	1550	
Mechanical property					
Tensile strength	23℃	ISO 527-1,2	MPa	95	
Elongation at Break	23℃	ISO 527-1,2	%	3.1	
Tensile Modulus	23℃	ISO 527-1,2	GPa	6.6	
Flexural Strength	23℃	ISO 178	MPa	150	
Flexural Modulus	23℃	ISO 178	GPa	6.3	
Coefficient of friction (Without lubrication)	Vs metal	Suzuki Method	-	0.16	
Coefficient of friction	Vs metal	-	-	0.2	
Rockwell Hardness	23℃	ISO 2039-2	R Scale	-	
Charpy Impact Strength (V-notched)	23℃	ISO 179	kJ/m ²	8	
Charpy Impact Strength (Unnotched)	23℃	ISO 179	kJ/m ²	57	
Heat property					
Coef of Linear Thermal Expansion	-30~100℃	ISO 11359-2	×10 ⁻⁵ /℃	5	
Heat Deflection Temp Low Load	0.45MPa	ISO 75-1,2	℃	220	
Heat Deflection Temp High Load	1.82MPa	ISO 75-1,2	℃	207	
Flammability		UL94	rank/thickness m mt	V0(1/16")	
Electrical property					
Volume Resistivity		IEC 60093	Ω・m	-	
Dielectric Strength		IEC 60243-1	MV/m	-	
Dielectric Constant	23℃、60% RH、50Hz	IEC 60250	-	3.8	
Dielectric Constant	23℃、60% RH、1KHz	IEC 60250	-	3.8	
Dissipation Factor	23℃、60% RH、50Hz	IEC 60250	-	0.002	
Dissipation Factor	23℃、60% RH、1MHz	IEC 60250	-	0.02	
Arc resistance	W electrode	IEC 60950	sec	-	
Molding property					
Mold shrinkage(Machine Direction)	80×80×3mm t	Toray Method	%	0.4	
Mold shrinkage(Transverse Direction)	80×80×3mm t	Toray Method	%	0.9	
Bar Flow	250℃,93MPa,1mm t	Toray Method	×10 ⁻³ m	113	

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.