

Property	Test Condition	Test Method ISO	Units	Unreinforced
				High impact, Low warpage
				VX10
				>PBT+ABS<
Physical property				
Density	23℃	ISO1183	kg/m ³	1135
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	46
Elongation at Break	23℃	ISO527-1,2	%	34
Tensile Modulus	23℃	ISO527-1,2	GPa	2.2
Flexural Strength	23℃	ISO178	MPa	66
Flexural Modulus	23℃	ISO178	GPa	2.1
Coefficient of friction (Without lubrication)	Vs metal	Suzuki Method	-	-
Coefficient of friction	Vs metal	-	-	-
Rockwell Hardness	23℃	ISO2039-2	R Scale	-
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	43
Charpy Impact Strength (Unnotched)	23℃	ISO179	kJ/m ²	-
Heat property				
Coef of Linear Thermal Expansion	-30~100℃	ISO11359-2	×10 ⁻⁵ /℃	-
Heat Deflection Temp Low Load	0.45MPa	ISO75-1,2	℃	-
Heat Deflection Temp High Load	1.82MPa	ISO75-1,2	℃	-
Flammability		UL94	rank/thickness m mt	HBEquivalent
Electrical property				
Volume Resistivity		IEC60093	Ω · m	-
Dielectric Strength		IEC60243-1	MV/m	-
Dielectric Constant	23℃、60% RH、50Hz	IEC 60250	-	-
Dielectric Constant	23℃、60% RH、1KHz	IEC 60250	-	-
Dissipation Factor	23℃、60% RH、50Hz	IEC 60250	-	-
Dissipation Factor	23℃、60% RH、1MHz	IEC 60250	-	-
Arc resistance	W electrode	IEC60950	sec	-
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	1.1
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	1.2
Bar Flow	250℃,93MPa,1mmt	Toray Method	×10 ⁻³ m	-

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.