

Property	Test Condition	Test Method ISO	Units	GF+Mineral filler reinforced
				High filler, High strength, High flow
				A305MD1
				>PPS-GF+MD50<
Physical property				
Water Absorption	24hrs. in 23℃ water	ISO62	%	0.02
Density	23℃	ISO1183	kg/m ³	1750
Color				Natural/Black
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	180
Elongation at Break	23℃	ISO527-1,2	%	1.3
Flexural Strength	23℃	ISO178	MPa	260
Flexural Modulus	23℃	ISO178	GPa	17
Coefficient of friction	Vs metal	-	-	-
Shear Strength	23℃	JIS K7214	MPa	-
Rockwell Hardness		ISO2039-2	R Scale	122
Taper Abrasion		ISO9352	mg/1000times	-
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	8
Charpy Impact Strength (Unnotched)	23℃	ISO179	kJ/m ²	40
Heat property				
Melting Point		ISO11357-3	℃	278
Coef of Linear Thermal Expansion	Machine Direction	ISO11359-2	×10 ⁻⁵ /K	1.8
Coef of Linear Thermal Expansion	Transverse Direction	ISO11359-2	×10 ⁻⁵ /K	3
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	℃	260
Flammability		UL94	rank/thickness mm	V-0Equivalent (0.35mm)
Electrical property				
Volume Resistivity		IEC60093	Ω · m	10 ¹⁴
Dielectric Strength		IEC60243-1	MV/m	24
Dielectric Constant	23℃、60%RH、1MHz	IEC 60250	-	5
Dissipation Factor	23℃、60%RH、1MHz	IEC 60250	-	0.002
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.16
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.75
Bar Flow	320℃,98MPa,1mmt	Toray Method	×10 ⁻³ m	120

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.