

Property	Test Condition	Test Method ISO	Units	GF+Mineral filler reinforced
				High filler, Epoxy adhesive bonding
				A610EA1
				>PPS-GF+MD60<
Physical property				
Water Absorption	24hrs. in 23℃ water	ISO62	%	0.02
Density	23℃	ISO1183	kg/m ³	1900
Color				Natural/Black
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	150
Elongation at Break	23℃	ISO527-1,2	%	0.8
Flexural Strength	23℃	ISO178	MPa	235
Flexural Modulus	23℃	ISO178	GPa	22
Coefficient of friction	Vs metal	-	-	-
Shear Strength	23℃	JIS K7214	MPa	-
Rockwell Hardness		ISO2039-2	R Scale	123
Taper Abrasion		ISO9352	mg/1000times	-
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	11
Charpy Impact Strength (Unnotched)	23℃	ISO179	kJ/m ²	18
Heat property				
Melting Point		ISO11357-3	℃	278
Coef of Linear Thermal Expansion	Machine Direction	ISO11359-2	×10 ⁻⁵ /K	1.6
Coef of Linear Thermal Expansion	Transverse Direction	ISO11359-2	×10 ⁻⁵ /K	2.3
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	℃	260
Flammability		UL94	rank/thickness mmt	V-0 (0.36mmt)
Electrical property				
Volume Resistivity		IEC60093	Ω · m	10 ¹⁴
Dielectric Strength		IEC60243-1	MV/m	23
Dielectric Constant	23℃、60%RH、1MHz	IEC 60250	-	-
Dissipation Factor	23℃、60%RH、1MHz	IEC 60250	-	-
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.15
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.7
Bar Flow	320℃,98MPa,1mmt	Toray Method	×10 ⁻³ m	150

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.