

Property	Test Condition	Test Method ISO	Units	Unreinforced
				Unreinforced, Standard
				A900
				>PPS<
Physical property				
Water Absorption	24hrs. in 23°C water	ISO 62	%	0.02
Density	23°C	ISO 1183	kg/m ³	1340
Color				Natural/Black
Mechanical property				
Tensile strength	23°C	ISO 527-1,2	MPa	85
Elongation at Break	23°C	ISO 527-1,2	%	8
Flexural Strength	23°C	ISO 178	MPa	140
Flexural Modulus	23°C	ISO 178	GPa	3.9
Coefficient of friction	Vs metal	-	-	-
Shear Strength	23°C	JIS K 7214	MPa	-
Rockwell Hardness		ISO 2039-2	R Scale	-
Taper Abrasion		ISO 9352	mg/1000times	-
Charpy Impact Strength (V-notched)	23°C	ISO 179	kJ/m ²	4
Charpy Impact Strength (Unnotched)	23°C	ISO 179	kJ/m ²	50
Heat property				
Melting Point		ISO 11357-3	°C	278
Coef of Linear Thermal Expansion	Machine Direction	ISO 11359-2	×10 ⁻⁵ /K	6.2
Coef of Linear Thermal Expansion	Transverse Direction	ISO 11359-2	×10 ⁻⁵ /K	6.6
Heat Deflection Temp High Load	1.80MPa	ISO 75-1,2	°C	105
Flammability		UL94	rank/thickness m mt	V-0Equivalent
Electrical property				
Volume Resistivity		IEC 60093	Ω · m	10 ¹⁴
Dielectric Strength		IEC 60243-1	MV/m	30
Dielectric Constant	23°C、60% RH、1MHz	IEC 60250	-	3.5
Dissipation Factor	23°C、60% RH、1MHz	IEC 60250	-	0.001
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	1.4
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	1.9
Bar Flow	320°C,98MPa,1mmt	Toray Method	×10 ⁻³ m	200

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.