

## 【Inquiries】

AsahiKASEI Engineering Plastics Information Comprehensive Site  
URL : <https://www.asahi-kasei-plastics.com/en/contact/>



## XYRON™ DV166

### Asahi Kasei Corporation - Polyphenylene Sulfide + PPE

Tuesday, February 15, 2022

#### General Information

##### Product Description

Modified PPE  
PPS/PPE alloy  
60% Filler reinforced Flame retardant V-1

##### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• Asia Pacific
Filler / Reinforcement	• Filler, 60% Filler by Weight		
Additive	• Flame Retardant		
Features	• Flame Retardant		
Processing Method	• Injection Molding		
Part Marking Code (ISO11469) (ISO 11469)	• >PPS+PPE-(GF+MD)60FR(40)<		

#### ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.82	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup> (2.00 mm)	0.10 to 0.20	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	87.0	MPa	ISO 527
Tensile Strain (Break, 23°C)	1.0	%	ISO 527
Flexural Modulus (23°C)	18100	MPa	ISO 178
Flexural Stress (23°C)	143	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>3</sup> (23°C)	6.0	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	256	°C	
CLTE			ISO 11359-2
Flow : -30 to 65°C	1.4E-5	cm/cm/°C	
Transverse : -30 to 65°C	3.1E-5	cm/cm/°C	

##### Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.
- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.
- Do not use plastics in any of the following orally- or medically-related applications.
- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages. For drinking water application, please consult Asahi Kasei Corporation.
- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

# XYRON™ DV166

## Asahi Kasei Corporation - Polyphenylene Sulfide + PPE

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	4.80		
1 MHz	4.20		
Dissipation Factor			IEC 60250
100 Hz	0.021		
1 MHz	0.013		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (2.5 mm)	V-1		UL 94

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	300 to 330	°C
Mold Temperature	90 to 130	°C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 150x150x2 mm

<sup>3</sup> 4 mm

### Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.