


TEREZ PA 6.6 7530 GF 30 HY

PA66

Ter Plastics

Product Texts

Medium viscosity industrial quality, 30% glassfiber reinforced, heat and hydrolysis resistant.
 For moulding parts with high stiffness at good heat stabilisation.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8200	MPa	ISO 527-1/-2
Stress at break	145	MPa	ISO 527-1/-2
Strain at break	2.2	%	ISO 527-1/-2
Charpy impact strength (+23°C)	55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	230	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	245	°C	ISO 75-1/-2
Other properties			
ISO Data			
Density	1340	kg/m ³	ISO 1183