



creative thermoplastic compounds

## Bondyram® 7103

Release Date: 10/09/2012

### **Maleic Anhydride Modified Ethylene-Alpha Olefin Copolymer.**

High flow impact modifier for Polyamide compounds un-reinforced and glass fiber reinforced. Good retention of impact at low temperatures.

**ISO**

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/m <sup>3</sup>	ISO-1183	0.88
MFI	g/10min	ISO-1133 190°C/2.16	1.5

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.

Moshav Ram - On ISRAEL 19205 Tel: +972 4 6599900 Fax: +972 4 6499763.  
Copyright © 2008 Polyram. All Rights Reserved. Created by Catom web design