



creative thermoplastic compounds

## PA301G50

Release Date: 31/12/2012

**Heat Stabilized, 50% Glass Fiber Reinforced Polyamide 6.6 for Injection Moulding applications.**  
**ISO**

| PHYSICAL PROPERTIES                               | UNIT              | TEST METHOD | VALUES           |
|---------------------------------------------------|-------------------|-------------|------------------|
| DENSITY                                           | g/cm <sup>3</sup> | ISO-1183    | 1.55             |
| WATER ABSORPTION (SATURATION)                     | %                 | ISO-62      | 4                |
| MOISTURE ABSORPTION<br>23° C, 50% RH (SATURATION) | %                 | ISO-62      | 1.2              |
| MOULD SHRINKAGE                                   | %                 | ISO-2577    | 0.1-0.5          |
| MECHANICAL PROPERTIES                             | UNIT              | TEST METHOD | VALUES           |
| TENSILE YIELD STRENGTH                            | MPa               | ISO-527     | 230              |
| TENSILE MODULUS                                   | MPa               | ISO-527     | 16000            |
| STRAIN @ BREAK                                    | %                 | ISO-527     | 2.5              |
| FLEXURAL STRENGTH                                 | MPa               | ISO-178     | 330              |
| FLEXURAL MODULUS                                  | MPa               | ISO-178     | 15000            |
| NOTCHED IZOD IMPACT STRENGTH +23°C                | Kj/m <sup>2</sup> | ISO-180     | 15               |
| NOTCHED CHARPY IMPACT STRENGTH +23°C              | Kj/m <sup>2</sup> | ISO-179     | 17               |
| UN NOTCHED CHARPY IMPACT STRENGTH<br>+23°C        | Kj/m <sup>2</sup> | ISO-179     | 90               |
| ROCKWELL HARDNESS                                 |                   | R scale     | 122              |
| THERMAL PROPERTIES                                | UNIT              | TEST METHOD | VALUES           |
| HDT AT LOAD 1.8 Mpa                               | °C                | ISO-75      | 250              |
| HDT AT LOAD 0.45 Mpa                              | °C                | ISO-75      | 255              |
| G.W.F.I                                           | °C                | IEC 60695   | 750              |
| UL FLAMMABILITY                                   |                   | UL-94 3mm   | H.B.             |
| MELTING POINT                                     | °C                | ISO-11357   | 256              |
| MAX TEMP CONTINUOUS USE                           | °C                |             | 130              |
| MAX TEMP SHORT<br>PEAKS OPERATION                 | °C                |             | 240              |
| ELECTRICAL PROPERTIES                             | UNIT              | TEST METHOD | VALUES           |
| SURFACE RESISTANCE                                | Ohm               | IEC 60093   | 10 <sup>12</sup> |
| VOLUME RESISTANCE                                 | Ohm x m           | IEC 60093   | 10 <sup>15</sup> |
| DIELECTRIC STRENGTH                               | kV/mm             | IEC 60250   | 90               |
| DIELECTRIC CONSTANT AT 1MHZ                       | kV/mm             | IEC 60250   | 3.8              |

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.