



creative thermoplastic compounds

RA303G33

Release Date: 22/01/2013

33% Glass Fiber Reinforced Heat Stabilized and Hydrolysis Resistant Polyamide 6.6 for Injection Moulding applications.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/m ³	ISO-1183	1.38
WATER ABSORPTION (SATURATION)	%	ISO-62	5.6
MOISTURE ABSORPTION 23° C, 50% RH (SATURATION)	%	ISO-62	1.7
MOULD SHRINKAGE	%	ISO-2577	0.3-0.4
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	200
TENSILE MODULUS	MPa	ISO-527	9200
STRAIN @ BREAK	%	ISO-527	3
FLEXURAL STRENGTH	MPa	ISO-178	295
FLEXURAL MODULUS	MPa	ISO-178	8100
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	16
NOTCHED IZOD IMPACT STRENGTH -30°C	Kj/m ²	ISO-180	10
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	250
HDT AT LOAD 0.45 Mpa	°C	ISO-75	250
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	256
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
SURFACE RESISTANCE	Ohm	IEC 60093	10 ¹³
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹⁵
DIELECTRIC STRENGTH	kV/mm	IEC 60250	90
DIELECTRIC CONSTANT AT 1MHZ	kV/mm	IEC 60250	3.7

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.