



creative thermoplastic compounds

## RA303G50

Release Date: 22/01/2013

**50% Glass Fiber Reinforced, Heat Stabilized and Hydrolysis Resistant Polyamide 6.6 for Injection Moulding applications.**

ISO

| PHYSICAL PROPERTIES                               | UNIT              | TEST METHOD | VALUES           |
|---------------------------------------------------|-------------------|-------------|------------------|
| DENSITY                                           | g/m <sup>3</sup>  | ISO-1183    | 1.45             |
| WATER ABSORPTION (SATURATION)                     | %                 | ISO-62      | 4                |
| MOISTURE ABSORPTION<br>23° C, 50% RH (SATURATION) | %                 | ISO-62      | 1.6              |
| MOULD SHRINKAGE                                   | %                 | ISO-2577    | 0.1-0.2          |
| MECHANICAL PROPERTIES                             | UNIT              | TEST METHOD | VALUES           |
| TENSILE YIELD STRENGTH                            | MPa               | ISO-527     | 215              |
| STRAIN @ BREAK                                    | %                 | ISO-527     | 3                |
| FLEXURAL STRENGTH                                 | MPa               | ISO-178     | 300              |
| FLEXURAL MODULUS                                  | MPa               | ISO-178     | 10000            |
| NOTCHED IZOD IMPACT STRENGTH +23°C                | KJ/m <sup>2</sup> | ISO-180     | 17               |
| ROCKWELL HARDNESS                                 |                   | R scale     | 122              |
| THERMAL PROPERTIES                                | UNIT              | TEST METHOD | VALUES           |
| HDT AT LOAD 1.8 Mpa                               | °C                | ISO-75      | 250              |
| HDT AT LOAD 0.45 Mpa                              | °C                | ISO-75      | 260              |
| UL FLAMMABILITY                                   |                   | UL-94 3mm   | H.B.             |
| MELTING POINT                                     | °C                | ISO-11357   | 256              |
| ELECTRICAL PROPERTIES                             | UNIT              | TEST METHOD | VALUES           |
| SURFACE RESISTANCE                                | Ohm               | IEC 60093   | 10 <sup>12</sup> |
| VOLUME RESISTANCE                                 | Ohm x m           | IEC 60093   | 10 <sup>15</sup> |
| DIELECTRIC STRENGTH                               | kV/mm             | IEC 60250   | 90               |
| DIELECTRIC CONSTANT AT 1MHZ                       | kV/mm             | IEC 60250   | 3.5              |

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.