



creative thermoplastic compounds

Polytron A50B01

Release Date: 09/02/2014

50% Long Glass Fiber Reinforced Black Nylon 6.6, Heat Stabilized for Injection Moulding application.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/m ³	ISO-1183	1.58
WATER ABSORPTION (SATURATION)	%	ISO-62	3
MOISTURE ABSORPTION 23° C, 50% RH (SATURATION)	%	ISO-62	1
MOULD SHRINKAGE	%	ISO-2577	0.1-0.3
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	230
TENSILE MODULUS	MPa	ISO-527	16000
STRAIN @ BREAK	%	ISO-527	1.9
FLEXURAL STRENGTH	MPa	ISO-178	350
FLEXURAL MODULUS	MPa	ISO-178	16500
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	27
NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	26
NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	23
UN NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	90
UN NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	70
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	253
UL FLAMMABILITY		UL-94 3mm	H.B.

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.