



creative thermoplastic compounds

PF320G2/PF321G2

Release Date: 25/05/2003

10% Glass Fiber Reinforced, Flame Retardant PBT for Injection Moulding applications.
ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.52
WATER ABSORPTION (SATURATION)	%	ISO-62	0.4
MOISTURE ABSORPTION 23° C, 50% RH (SATURATION)	%	ISO-62	0.2
MOULD SHRINKAGE	%	ISO-2577	1.3
MFI	g/10min	ISO-1133 250/2.16	20
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	80
STRAIN @ BREAK	%	ISO-527	3
FLEXURAL STRENGTH	MPa	ISO-178	120
FLEXURAL MODULUS	MPa	ISO-178	4800
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	5
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	210
HDT AT LOAD 0.45 Mpa	°C	ISO-75	220
G.W.F.I	°C	IEC 60695	750
UL FLAMMABILITY		UL-94 3mm	V-0
MELTING POINT	°C	ISO-11357	225
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹⁶
DIELECTRIC STRENGTH	kV/mm	IEC 60250	29
DIELECTRIC CONSTANT AT 1MHZ	kV/mm	IEC 60250	3.4

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.