



creative thermoplastic compounds

PF350M3

Release Date: 08/07/2003

15% Mineral Filled PBT for Injection Moulding applications.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.41
WATER ABSORPTION (SATURATION)	%	ISO-62	0.5
MOULD SHRINKAGE	%	ISO-2577	1.8
MFI	g/10min	ISO-1133 250/2.16	20
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	55
STRAIN @ BREAK	%	ISO-527	15
FLEXURAL STRENGTH	MPa	ISO-178	95
FLEXURAL MODULUS	MPa	ISO-178	3000
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	6
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	225
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DIELECTRIC CONSTANT AT 1MHZ	kV/mm	IEC 60250	3.6

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.