



creative thermoplastic compounds

PF321G6

Release Date: 14/12/2011

30% Glass Fiber Reinforced, Flame Retardant PBT/PET for Injection Moulding application.
ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.68
WATER ABSORPTION (SATURATION)	%	ISO-62	0.5
MOISTURE ABSORPTION 23° C, 50% RH (SATURATION)	%	ISO-62	0.1
MOULD SHRINKAGE	%	ISO-2577	0.2
MFI	g/10min	ISO-1133 250/2.16	10
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	140
TENSILE MODULUS	MPa	ISO-527	9400
STRAIN @ BREAK	%	ISO-527	3
FLEXURAL STRENGTH	MPa	ISO-178	170
FLEXURAL MODULUS	MPa	ISO-178	8000
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	9
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	210
HDT AT LOAD 0.45 Mpa	°C	ISO-75	220
G.W.F.I	°C	IEC 60695	960
UL FLAMMABILITY		UL-94 3+1.6mm	V-0/5VA
MELTING POINT	°C	ISO-11357	225
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DIELECTRIC CONSTANT AT 1MHZ	kV/mm	IEC 60250	3.6

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.