



creative thermoplastic compounds

PE321G6NT

Release Date: 19/07/2012

30% Glass Fiber Reinforced, Flame Retardant V-0 PET for Injection Moulding applications.
ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/m ³	ISO-1183	1.67
MOULD SHRINKAGE	%	ISO-2577	0.3
MFI	g/10min	ISO-1133 280/2.16	6
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	125
STRAIN @ YIELD	%	ISO-527	11160
STRAIN @ BREAK	%	ISO-527	3
FLEXURAL STRENGTH	MPa	ISO-178	210
FLEXURAL MODULUS	MPa	ISO-178	10000
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	8.5
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	224
HDT AT LOAD 0.45 Mpa	°C	ISO-75	245
G.W.F.I	°C	IEC 60695	960
UL FLAMMABILITY		UL-94 0.4/0.8/3mm	V-0
MELTING POINT	°C	ISO-11357	254
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
CTI		IEC 60112	250

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.