



creative thermoplastic compounds

PM1009

Release Date: 03/04/2013

General Purpose Polyacetal Copolymer for Injection Moulding applications. MFI 9.
ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.41
MOULD SHRINKAGE	%	ISO-2577	1.8-2.2
MFI	g/10min	ISO-1133 190/2.16	9
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	60
STRAIN @ BREAK	%	ISO-527	60
FLEXURAL STRENGTH	MPa	ISO-178	80
FLEXURAL MODULUS	MPa	ISO-178	2600
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	7
ROCKWELL HARDNESS		R scale	82
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	110
HDT AT LOAD 0.45 Mpa	°C	ISO-75	160
VICAT SOFTENING POINT	°C	ISO-306	134
FLAMMABILITY	mm/min	FMVSS302	17
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	165
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
SURFACE RESISTANCE	Ohm	IEC 60093	10 ¹⁴
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹⁶
DIELECTRIC STRENGTH	kV/mm	IEC 60250	24
DIELECTRIC CONSTANT AT 1MHZ	kV/mm	IEC 60250	3.8

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.