



creative thermoplastic compounds

PM1419/PM1429

Release Date: 03/04/2013

Polyacetal filled with PTFE for sliding parts, Low Friction and improved Wear Resistance of moulded parts.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.45-1.50
MOULD SHRINKAGE	%	ISO-2577	1.8-2.2
MFI	g/10min	ISO-1133 190/2.16	9
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	50
TENSILE MODULUS	MPa	ISO-527	2000
STRAIN @ BREAK	%	ISO-527	35
FLEXURAL STRENGTH	MPa	ISO-178	70
FLEXURAL MODULUS	MPa	ISO-178	1900
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	4
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	120
HDT AT LOAD 0.45 Mpa	°C	ISO-75	155
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	165
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
SURFACE RESISTANCE	Ohm	IEC 60093	10 ¹⁴
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹⁶

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.