



creative thermoplastic compounds

PM3009G5

Release Date: 03/04/2013

25% Glass Fiber Reinforced Polyacetal for Injection Moulding applications.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.58
MOULD SHRINKAGE	%	ISO-2577	0.4-1
MFI	g/10min	ISO-1133 190/2.16	4
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	100
STRAIN @ BREAK	%	ISO-527	2
FLEXURAL STRENGTH	MPa	ISO-178	150
FLEXURAL MODULUS	MPa	ISO-178	3400
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	5.4
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	165
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
SURFACE RESISTANCE	Ohm	IEC 60093	10 ¹²
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹⁴
DIELECTRIC STRENGTH	kV/mm	IEC 60250	20

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.