



creative thermoplastic compounds

PM8427

Release Date: 03/04/2013

Impact Modified Polyacetal for Injection Moulding applications. MFI 9.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.38
MOULD SHRINKAGE	%	ISO-2577	1.8-2.2
MFI	g/10min	ISO-1133 190/2.16	9
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	40
STRAIN @ BREAK	%	ISO-527	70
FLEXURAL STRENGTH	MPa	ISO-178	60
FLEXURAL MODULUS	MPa	ISO-178	2100
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	11.5
ROCKWELL HARDNESS		R scale	77
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	85
HDT AT LOAD 0.45 Mpa	°C	ISO-75	145
FLAMMABILITY	mm/min	FMVSS302	31.5
UL FLAMMABILITY		UL-94 3mm	HB
MELTING POINT	°C	ISO-11357	165
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
SURFACE RESISTANCE	Ohm	IEC 60093	10 ¹²
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹³
DIELECTRIC STRENGTH	kV/mm	IEC 60250	24
DIELECTRIC CONSTANT AT 1MHZ	kV/mm	IEC 60250	4.2

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.