



creative thermoplastic compounds

Bondyram® 1001CN

Release Date: 10/09/2012

Maleic Anhydride Modified Copolymer Polypropylene.

Recommended for coupling of glass and other fillers in polypropylene composites.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	0.90
MFI	g/10min	ISO-1133 190°C/2.16	100
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
MELTING POINT	°C	ISO-11357	167

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.