



creative thermoplastic compounds

Polytron P30B01

Release Date: 09/02/2014

A Chemically Coupled 30% Long Glass Fiber Reinforced Black Polypropylene, Heat Stabilized for High Temperature applications such as under the hood automotive parts.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.12
MOULD SHRINKAGE	%	ISO-2577	0.2-0.4
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	105
TENSILE MODULUS	MPa	ISO-527	7000
STRAIN @ BREAK	%	ISO-527	2.0
FLEXURAL STRENGTH	MPa	ISO-178	155
FLEXURAL MODULUS	MPa	ISO-178	6600
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	18
NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	17
NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	16
UN NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	55
UN NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	35
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	157
G.W.F.I	°C	IEC 60695	750
FLAMMABILITY	mm/min	FMVSS302	30@2mm
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	167

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.