



creative thermoplastic compounds

Polytron P50B07/P50B07-S (single strand)

Release Date: 02/02/2014

A Chemically Coupled 50% Long Glass Fiber Reinforced Black Polypropylene, Heat Stabilized, UV Stabilized for Injection Moulding applications.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/m ³	ISO-1183	1.33
MOULD SHRINKAGE	%	ISO-2577	0.2-0.3
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	135
TENSILE MODULUS	MPa	ISO-527	12500
STRAIN @ BREAK	%	ISO-527	1.6
FLEXURAL STRENGTH	MPa	ISO-178	210
FLEXURAL MODULUS	MPa	ISO-178	12000
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	25
NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	25
NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	22
UN NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	60
UN NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	45
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	152
G.W.F.I	°C	IEC 60695	750
FLAMMABILITY	mm/min	FMVSS302	20
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	168

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.