



creative thermoplastic compounds

PPC372B73

Release Date: 03/04/2013

73% Mineral Filled Polypropylene for Heavy Density Injection Moulding applications.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/m ³	ISO-1183	2.1
MOULD SHRINKAGE	%	ISO-2577	0.8-1.2
MFI	g/10min	ISO-1133 230/2.16	20
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	10
TENSILE MODULUS	MPa	ISO-527	1700
STRAIN @ BREAK	%	ISO-527	>10
FLEXURAL STRENGTH	MPa	ISO-178	20
FLEXURAL MODULUS	MPa	ISO-178	2200
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	10

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.