



creative thermoplastic compounds

PN300G6

Release Date: 19/09/2006

PPE/PS Alloy 30% Glass Fiber Reinforced for Injection Moulding applications.

ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/m ³	ISO-1183	1.3
WATER ABSORPTION (SATURATION)	%	ISO-62	0.2
MOISTURE ABSORPTION 23° C, 50% RH (SATURATION)	%	ISO-62	0.06
MOULD SHRINKAGE	%	ISO-2577	0.1-0.3
MFI	g/10min	ISO-1133 280/10	5
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	90
TENSILE MODULUS	MPa	ISO-527	7900
STRAIN @ BREAK	%	ISO-527	3
FLEXURAL STRENGTH	MPa	ISO-178	130
FLEXURAL MODULUS	MPa	ISO-178	7300
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	10
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
UL FLAMMABILITY		UL-94 3mm	H.B.
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
SURFACE RESISTANCE	Ohm	IEC 60093	10 ¹⁵
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹⁵
DIELECTRIC STRENGTH	kV/mm	IEC 60250	18

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.