



3220 Crocker Avenue, Sheboygan, WI 53081
Tel 920.803.0778 | Fax 920.803.0779
www.sacopolymers.com

Customized Solutions for Diverse Applications

0103-212a NT

Non-halogen flame retardant compound

Description

Macromeric® 0103-212a NT is a natural, UV resistant, non-halogen flame retardant RoHS polyolefin compound. It is designed for use in a wide variety of jacketing applications including wire and cable and tube bundles. This compound has superior fire performance; including slow flame propagation, self-extinguishing characteristics, and low smoke production. Macromeric® 0103-212a NT should be extruded with a screw configuration designed to optimize process conditions and throughput. This extrusion compound meets, or exceeds, several industry jacketing specifications, including UL 1277 tray cable.

Properties	Conditions	Typical Value	Unit	Test Method
Physical				
Specific Gravity	at 23°C	1.51	g/cm3	ASTM D792
Melt Index	190°C, 21.6 kg	3.0	g/10-min.	ASTM D1238
Tear Strength	at 23°C	320	lbf/in.	ASTM D470
Low Temperature Brittleness	3 minutes in methanol	-30	°C	ASTM D746-07
Mechanical				
Tensile Strength	at break	2000	psi	ASTM D638
	Air, 7-days at 136°C	110	% Retention	
	Air, 14-days at 121°C	110	% Retention	
Elongation	at break	200	%	ASTM D638
	Air, 7-days at 136°C	75	% Retention	
	Air, 14-days at 121°C	75	% Retention	
UL 1581, Section 481	Air, 150-days at 97°C	90	Rating, °C	UL 1581
Deformation Test	2000-gram load, 121°C	5.4	% deformation	UL 1277
Flexural Modulus	1% secant	25,000	psi	ASTM D790
Hardness				
Durometer	1-second	90	Shore A	ASTM D2240
Flammability				
Ash Content	Procedure B	44	%	ASTM D5630
LOI	23°C	35	%	ASTM D-2863
NBS Smoke Density	Smoldering Mode	225	Dm(corr.)	ASTM E-662
	Flaming Mode	30	Dm(corr.)	ASTM E-662

The technical information contained herein is, to the best of our knowledge, believed to be accurate. However, Säco Polymers makes no guarantee or warranty, and does not assume any liability, with respect to the accuracy or completeness of such information. Suitability of material for a specific final end use is the sole responsibility of the user. The data contained herein are typical properties only and are not be used as specifications. (rev 11/18/2010)

Processing

Macromeric® 0103-212a NT can be processed very easily on a wide range of commercially available extrusion equipment. It can withstand extrusion temperatures up to 425°F, but recommended temperatures are much lower. A typical temperature profile would be:

Processing Conditions

Zone 1:	300 - 320°F
Zone 2:	330 - 350°F
Zone 3:	350 - 370°F
Zone 4:	350 - 370°F
Head:	340 - 360°F
Die:	370 - 390°F
Melt Temperature:	360 - 380°F

It is recommended that Macromeric® 0103-212a NT is pre-dried in a heated desiccant system prior to processing. As processes vary widely, please call for specific requirements for your application(s).

Storage

Saco Polymers recommends that Macromeric® 0103-212a NT be stored in an ambient temperature range (40 to 80 degrees Fahrenheit), tightly sealed in its original container and away from moisture and high humidity.

Packaging

0103-212a NT is packaged at 2,000-pounds in foil-lined 41 ft³ octagon gaylords (39.5 inches in height).



3220 Crocker Avenue, Sheboygan, WI 53081
Tel 920.803.0778 | Fax 920.803.0779
www.sacopolymers.com

The technical information contained herein is, to the best of our knowledge, believed to be accurate. However, Saco Polymers makes no guarantee or warranty, and does not assume any liability, with respect to the accuracy or completeness of such information. Suitability of material for a specific final end use is the sole responsibility of the user. The data contained herein are typical properties only and are not be used as specifications. (rev. 11/18/2010)