



TER Plastics
POLYMER GROUP



Starex BF-0370

ABS

Samsung Cheil Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index	18	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Density, 73°F	1060	kg/m³	ASTM D 792
Mechanical properties			
ASTM Data			
Tensile Strength	51	MPa	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	2450	MPa	ASTM D 790
Flexural Strength	76	MPa	ASTM D 790
Rockwell Hardness	R 112	-	ASTM D 785
Izod Impact notched, 1/8 in	0.141	kJ/m	ASTM D 256
Thermal properties			
ISO Data			
Vicat softening temperature, 50°C/h 50N	102	°C	ISO 306
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	89	°C	ASTM D 648

Characteristics

Delivery form

Pellets, Natural Color

Features

Low Odor