



TEREZ ABS 3016 UV

ABS

Ter Plastics

Product Texts

Easy flowing ABS-Type with good impact resistance and UV-stabilizer.

For moulding parts with low wallthickness and/or unfavourable flow distances / wallthickness-relation.

Rheological properties	Value	Unit	Test Standard
------------------------	-------	------	---------------

ISO Data

Melt flow index, MFI	34	g/10min	ISO 1133
MFI temperature	220	°C	ISO 1133
MFI load	10	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
-----------------------	-------	------	---------------

ISO Data

Tensile Modulus	2300	MPa	ISO 527-1/-2
Yield stress	44	MPa	ISO 527-1/-2
Yield strain	2.4	%	ISO 527-1/-2
Strain at break	12	%	ISO 527-1/-2
Charpy impact strength (+23°C)	125	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	19	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
--------------------	-------	------	---------------

ISO Data

Temp. of deflection under load (1.80 MPa)	77	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	88	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	94	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
-----------------------	-------	------	---------------

ISO Data

Volume resistivity	1E13	Ohm*m	IEC 60093
--------------------	------	-------	-----------

Other properties	Value	Unit	Test Standard
------------------	-------	------	---------------

ISO Data

Water absorption	0.94	%	Sim. to ISO 62
Humidity absorption	0.23	%	Sim. to ISO 62
Density	1040	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Amorphous

Delivery form

Pellets

Applications

Automotive, Building Construction, IT / Business Machine, Encapsulation, Sports Equipment

Special Characteristics

Light stabilized or stable to light