



<b>Starex WX-9300</b>							
ASA							
<b>Processing/Physical Characteristics</b>		<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>			
<b>ASTM Data</b>							
Melt Flow Index	10	g/10min		ASTM D 1238			
Temperature	220	°C		-			
Load	10	kg		-			
Density, 73°F	1080	kg/m³		ASTM D 792			
<b>Mechanical properties</b>							
<b>ASTM Data</b>		<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>			
Tensile Strength at Yield	44	MPa		ASTM D 638			
Flexural Modulus	2200	MPa		ASTM D 790			
Flexural Strength	67	MPa		ASTM D 790			
Rockwell Hardness	R 105	-		ASTM D 785			
Izod Impact notched, 1/8 in	0.19	kJ/m		ASTM D 256			
<b>Thermal properties</b>							
<b>ISO Data</b>		<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>			
Vicat softening temperature, 50°C/h 50N	99	°C		ISO 306			
<b>Characteristics</b>							
<b>Delivery form</b>		<b>Features</b>					
Pellets, Natural Color		Low Odor					
<b>Special Characteristics</b>							
U.V. stabilized or stable to weather							