

**Stanyl® TW441**

PA46

DSM Engineering Plastics

Product Texts

High Viscosity, Heat Stabilized, Lubricated

ISO 1043 PA46

[Stanyl website](#)**Mechanical properties** dry / cond Unit Test Standard**ISO Data**

Tensile Modulus	3300 / 1000	MPa	ISO 527-1/-2
Yield stress	100 / 55	MPa	ISO 527-1/-2
Yield strain	10 / 20	%	ISO 527-1/-2
Nominal strain at break	40 / >50	%	ISO 527-1/-2
Tensile creep modulus, 1000h	* / 550	MPa	ISO 899-1
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 45	kJ/m ²	ISO 179/1eA

Thermal properties dry / cond Unit Test Standard**ISO Data**

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	280 / *	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	290 / *	°C	ISO 306
Coeff. of linear therm. expansion, parallel	85 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	110 / *	E-6/K	ISO 11359-1/-2
Oxygen index	27 / *	%	ISO 4589-1/-2

Electrical properties dry / cond Unit Test Standard**ISO Data**

Relative permittivity, 100Hz	3.9 / 22	-	IEC 60250
Relative permittivity, 1MHz	3.6 / 4.5	-	IEC 60250
Dissipation factor, 100Hz	70 / 8700	E-4	IEC 60250
Dissipation factor, 1MHz	260 / 1200	E-4	IEC 60250
Volume resistivity	1E13 / 1E7	Ohm*m	IEC 60093
Surface resistivity	* / 1E13	Ohm	IEC 60093
Electric strength	25 / 15	kV/mm	IEC 60243-1
Comparative tracking index	400 / -	-	IEC 60112

Other properties dry / cond Unit Test Standard**ISO Data**


Water absorption	13.5 / *	%	Sim. to ISO 62
Humidity absorption	3.7 / *	%	Sim. to ISO 62
Density	1180 / -	kg/m ³	ISO 1183

Material specific properties dry / cond Unit Test Standard**ISO Data**


Viscosity number	220 / *	cm ³ /g	ISO 307, 1157, 1628
------------------	---------	--------------------	---------------------

Diagrams


Dynamic Shear modulus-temperature




Stress-strain




Stress-strain




Secant modulus-strain




Secant modulus-strain




Stress-strain (isochronous) 23°C




Creep modulus-time 23°C




Stress-strain (isochronous) 100°C




Creep modulus-time 100°C




Stress-strain (isochronous) 140°C




Creep modulus-time 140°C



Stress-strain (isochronous) 160°C



Creep modulus-time 160°C



Characteristics

Processing

Injection Molding, Other Extrusion

Special Characteristics

Platable, Heat stabilized or stable to heat

Additives

Lubricants, Release agent

Other text information

Injection Molding

[Injection Molding Recommendations](#)